


New Jersey Department of Transportation

1035 Parkway Avenue, PO Box 600, Trenton, New Jersey 08625-0600



Baseline Document Change Announcement

Portland Cement Concrete Specifications

Subsections 106.03, 305.05, 905.02, 914.02, 914.04 and 914.05

BDC02S-08

February 7, 2003

SUBJECT: Revisions to Subsections **106.03, 305.05, 905.02, 914.02, 914.04 and 914.05** of the **2001 Standard Specifications for Road and Bridge Construction, Portland Cement Concrete – Statistical Specifications and also Elimination of Class “C” Concrete**

REFERENCE: This announcement must be used in conjunction with **[BDC02D-01](#)**, dated **February 6, 2003**, revising several **Roadway Construction Detail Sheets**

Subsections 106.03, 305.05, 905.02, 914.02, 914.04 and 914.05 of the *2001 Standard Specifications for Road and Bridge Construction* have been revised. The main revisions include acceptance procedures and revised pay adjustment schedules for Portland Cement Concrete, a revision addressing how bonuses and pay reductions are shared between Contractors and their Producers/Subcontractors, and the substitution of Class “C” Concrete with Class “B” Concrete. Additional revisions permit wider use of Type “F” admixtures and allow for the use of nondestructive testing prior to coring.

The revisions are incorporated into the Standard Specifications via SI2001E1 and SI2001M1. The changes to SI2001E1 are as follows:

SECTION 106 – CONTROL OF MATERIAL

106.03 Materials, Inspections, Tests, and Samples.

THE FOLLOWING SUBPART IS ADDED:

- D. Sharing of Pay-adjustments for Portland Cement Concrete.** Positive and negative pay-adjustments, as defined in Subsection 914.02, Subpart E, are awarded to encourage high quality construction and, when necessary, to recoup the anticipated extra costs to the Department resulting from poor quality construction. The manner in which positive and negative pay-adjustments are to be shared by the prime Contractor and Subcontractors or Producers is to be negotiated by the affected parties. A letter signed by both parties, stating that an agreement has been reached between the parties shall be provided to the Engineer before commencement of Work. Nothing contained herein shall create right of action either in law or equity against the Department.

SECTION 305 – CONCRETE BASE COURSE

305.05 Opening to Traffic.

THIS SUBSECTION IS CHANGED TO:

The opening to traffic shall be as specified in Subsection 405.20.

SECTION 405 – CONCRETE SURFACE COURSE

405.08 Mixing Concrete.

1. Mixing on the Project in Truck Mixers.

THIS FIRST SENTENCE IN THE 15TH PARAGRAPH IS CHANGED TO:

Each batch shall be mixed not less than 50 revolutions at the rate of rotation designated as mixing speed.

3. Transit Mixing.

THE 9TH PARAGRAPH IS CHANGED TO:

Mixing shall begin immediately following the complete charging of the drum and continue for not less than 50 revolutions of the drum at the mixing speed recommended by the manufacturer of the truck mixer. Upon completion of at least the minimum number of mixing revolutions at the plant, the speed of the drum shall be reduced to the agitation speed recommended by the manufacturer.

THE LAST PARAGRAPH IS CHANGED TO:

Transit mix concrete will be rejected for any of the following reasons:

- a. If the concrete is not discharged within the specified time limit after loading all ingredients into the drum;
- b. If the indicator on the counter shows that the instrument has been turned off or tampered with;
- c. If the non-resettable total revolution counter shows more than 300 revolutions;
- d. If water has been added while the truck mixer is en route to the Project. Two-way telephone or radio communication between the site of the placement of concrete and the batching plant shall be provided.

914.02 Portland Cement Concrete Design, Control, and Acceptance Testing Requirements.

B. Proportioning and Verification.

THE SECOND SENTENCE OF THE THIRD PARAGRAPH IS CHANGED TO:

At least six 4 by 8 inch test cylinders shall be prepared from each batch and cured according to AASHTO T 23 or AASHTO T 126.

THE FIRST SENTENCE OF THE TENTH PARAGRAPH IS CHANGED TO:

Classes A and B concrete may be designed to achieve early strength requirements by increasing the Cement content.

C. Acceptance Testing Procedures for Slump and Air Entrainment.

THE FIRST SENTENCE OF THE FOURTH PARAGRAPH IS CHANGED TO:

Following any permitted additions, the drum shall be rotated at the recommended mixing speed for a minimum of 30 revolutions without exceeding 300 total revolutions, the original test results shall be disregarded, and a single test for both slump and air entrainment performed.

D. General Acceptance Testing Requirements for Strength.

THE FOLLOWING IS ADDED AFTER THE SECOND PARAGRAPH:

Concrete test specimens which are to be used for determination of early strengths for form removal, opening to traffic, or otherwise placing the concrete into service shall be cured according to the field curing provisions in AASHTO T-23.

E. Acceptance Testing for Strength for Pay-Adjustment Items.

THE ENTIRE TEXT OF THIS SUBPART IS CHANGED TO:

The list of concrete Pay Items, if any, which are subject to pay-adjustment and their base prices may be found in the Special Provisions.

The amount of pay-adjustment in dollars is the product of the Pay Item base price times the lot quantity times the percent pay-adjustment (expressed as a decimal) given by Equation 1 or Equation 2.

Equation 1 and Equation 2:

Quality	Pay-adjustment (Percent)	
PD < 50	PPA = 3.0 - 0.3 PD	Equation 1
PD ≥ 50	PPA = 26.0 - 0.76 PD	Equation 2

Where: PPA = Percent Pay-adjustment
 PD = Percent Defective (Estimate of percent of lot below the class design strength by the use of Equation 3 and Subsection 914.05, Table 914-5)

Equation 3:

$$Q = (ALS - CDS) / S$$

Where: Q = Quality index for pay-adjustment computations
 ALS = Average lot strength in psi
 CDS = Class design strength in psi
 S = Standard deviation of the strength test results in psi for the lot as computed by Equation 4

Equation 4:

$$S = \sqrt{\frac{\sum(Xi - ALS)^2}{N - 1}}$$

Where: \sum = Summation
 Xi = Individual test result (average strength of a test cylinder pair)
 N = Number of test results for the lot

Note: When only a single test result is available, the standard deviation "S" is assumed to equal 200 psi.

For lots having percent defective (PD) levels less than 10 percent, Equation 1 provides positive adjustments to the contract price. For lots having exactly 10 percent defective, there is no adjustment to the contract price. For lots having greater than 10 percent defective, Equations 1 or 2, as appropriate, subtract progressively larger amounts from the contract price.

If, based on the initial series of tests, the lot quality of a pay-adjustment item is estimated to be PD = 50 or greater, or if any individual test value (average of a cylinder pair) falls below the retest limit for non-pay-adjustment concrete in Subsection 914.05, Table 914-4, the Engineer has the option to reevaluate by coring or other suitable means. When this provision is applied to Class P concrete, each beam or pile in the steam bed will be evaluated separately.

If the Department elects not to core, the Contractor may accept the pay-adjustment of (PPA) calculated by Equation 2 or, when approved by the Engineer, may take cores according to Subsection 914.05, Table 914-4 at no cost to the Department. The Contractor must take the cores within 60 days

from notification of the option to core. As an aid in making this decision, the Contractor will be permitted to perform nondestructive testing using a method or device approved by the Engineer.

When re-evaluation is accomplished by a method other than coring, the results will be used only to determine what further action is to be taken. If any of the non-core tests results are below the class design strength, the Engineer has the option to core. If this option is waived, the Contractor may elect to core, at no cost to the State and within 60 days after being presented with this option, or to accept the pay-adjustment computed from the initial test cylinder results. If the Contractor elects to core, the coring shall be performed as directed and the Department will test the cores. If none of the non-core test results is below the class design strength, the Engineer may elect either to core or to accept the lot at 100 percent payment.

If, based on the core results, the lot is determined to be at a quality level of $PD < 75$, the pay-adjustment shall be computed by Equation 1 or Equation 2, as appropriate. If the lot is confirmed to be at a quality level of $PD = 75$ or greater, the lot is considered to be rejectable and the Engineer may:

1. Require the Contractor to remove and replace the defective lot at no cost to the State,
2. Allow the Contractor to leave the defective lot in place and receive a percent pay-adjustment (PPA) computed by Equation 2, or
3. Allow the Contractor to submit a plan, for approval, for corrective action to be performed at no cost to the State. If the plan for corrective action is not approved, either option 1 or 2 above may be applied.

F. Acceptance Testing for Strength for Non-Pay-Adjustment Items.

THE ENTIRE TEXT OF THIS SUBPART IS CHANGED TO:

All concrete items not specifically designated as pay-adjustment items as described in Subsection 914.02, Subpart E are considered to be non-pay-adjustment items, but may be accepted by pay-adjustment under certain circumstances. Such an item is eligible for 100 percent payment ($PA = 0$) provided the retest limit of Subsection 914.05, Table 914-4 is met. If this requirement is not met, the item will be treated as a pay-adjustment item according to Subsection 914.02, Subpart E, and all pay-adjustment provisions shall apply except that the item bid price will be used instead of an item base price in the computation of the pay-adjustment.

When a pay-adjustment is computed for any of the following items, which are only partially composed of concrete, the amount of pay-adjustment, if any, will be multiplied by the Estimated Percentage of Concrete (expressed as a decimal) as indicated below:

Pay Item of Concrete	Estimated Percentage
INLETS, TYPE ____	30
INLETS, TYPE ____, USING EXISTING CASTING	30
INLETS, TYPE B-____	40
INLETS, TYPE B-____, USING EXISTING CASTING	40
INLETS, TYPE ____ MODIFIED	40
INLETS, TYPE ____ MODIFIED, USING EXISTING CASTING	40
INLETS, TYPE ES	50
INLET CASTINGS, TYPE ES	40
MANHOLES	30
MANHOLES, ____ ' DIAMETER	30
MANHOLES, USING EXISTING CASTING	30
MANHOLES, SANITARY SEWER	30
MANHOLES, SANITARY SEWER, USING EXISTING CASTING	30
GRANITE CURB	25
RESET GRANITE CURB	25
BEAM GUIDE RAIL ANCHORAGES	25
CHAIN-LINK FENCE, ____ ' HIGH	25
CHAIN-LINK FENCE, ALUMINUM-COATED STEEL, ____ ' HIGH	25
CHAIN-LINK FENCE, PVC-COATED STEEL, ____ ' HIGH	25
CHAIN-LINK FARM-TYPE FENCE	25
GATES, CHAIN-LINK FENCE, ____ ' WIDE	25

GATES, CHAIN-LINK FENCE, ALUMINUM-COATED STEEL, ___ ' WIDE	25
GATES, CHAIN-LINK FENCE, PVC-COATED STEEL, ___ ' WIDE	25
GATES, CHAIN-LINK FARM-TYPE FENCE, ___ ' WIDE	25
RESET FENCE	25
TEMPORARY CHAIN-LINK FENCE, ___ ' HIGH	25
GUIDE SIGNS, TYPE GA, BREAKAWAY SUPPORTS	20
GUIDE SIGNS, TYPE GA, NON-BREAKAWAY SUPPORTS	20

The amount of pay-adjustment for pay items not listed above is the product of the unit bid price times the lot quantity times the percent pay-adjustment given by Equation 1.

914.04 Sampling and Testing Methods.

THE FOLLOWING AASHTO TEST METHOD IS ADDED:

T303	Standard Test Method for Accelerated Detection of Potentially Deleterious Expansion of Mortar Bars Due to Alkali-Silica Reaction.
------	---

914.05 Tables

TABLES 914-1, 914-3, AND 914-4 ARE CHANGED TO:

Table 914-1 Requirements for Roadway Concrete Items

	Concrete Class	Slump (inch)	Percent Air Entrainment for Coarse Aggregate Size Numbers				
			357	467	57	67	8
Cast-in-Place Items							
Surface Course, Bridge Approach Slabs, Bridge Approach Transition Slabs	B	2±1	5.0±1.5	5.0±1.5	6.0±1.5	6.0±1.5	7.0±1.5
Base Course	B	2±1	5.0±1.5	5.0±1.5	6.0±1.5	6.0±1.5	7.0±1.5
Inlet and Manhole Walls, Headwalls, Miscellaneous Concrete	B	3±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Inlet and Manhole Top Slabs, Sidewalks, Driveways, Islands	B	3±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Slope Gutters, Vertical Curb, Sloping Curb, Barrier Curb and Base	B	4±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Concrete and White Concrete Vertical, Sloping and Barrier Curb, Concrete and White Concrete Islands	B	4±1	----	----	7.0±2.0	7.0±2.0	8.0±2.0
Foundations for:							
Inlets and Manholes	B	3±1	6.5 max	6.5 max	7.5 max	7.5 max	8.5 max
Electrical Items	B	3±1	----	----	7.5 max	7.5 max	8.5 max
Signs	B	3±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Junction Boxes	B	3±1	----	----	7.5 max	7.5 max	8.5 max

Table 914-1 (Continued)

	Concrete Class	Slump (inch)	Percent Air Entrainment for Coarse Aggregate Size Numbers				
			357	467	57	67	8
Cast-in-Place Items (continued)							
Footings for Fence Posts, Guide Rail End Treatment	B	3±1	----	----	7.5 max	7.5 max	8.5 max
Culverts	A	3±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Monuments	A	3±1	----	----	7.5 max	7.5 max	8.5 max
Slope Protection	B	2±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Precast Items							
Culverts	A	3±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Inlets and Manholes, Junction Boxes, Headwalls, Reinforced Concrete End Sections (See note 2)	B	3±1	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Concrete and White Concrete Barrier Curb	B	3±1	----	----	7.0±2.0	7.0±2.0	8.0±2.0

Note 1: According to Subsection 501.03, a Type F water-reducing, high range admixture will be permitted according to Subsection 905.02 and Subsection 914.02, Subparts B and C. When a Type F admixture is used, the table Slump and Air Content values for the given concrete item shall be changed as follows:

Slump: 6 ± 2 inches

Air Content: Increase both the target value and tolerance percentages by 0.5.

Note 2: For the items in this category, the slump may be reduced to zero (dry cast) provided that adequate consolidation, acceptable to the Engineer, is achieved.

Table 914-3 Mix Design Requirements

	Class of Concrete					
	A	B	S	P	P-1	P-2
Class Design Strength (28 days, psi Note 3)	4600	3700	2000	5500	6000	6500
Verification Strength (28 days, psi Note 3)	5400	4500	--	6000	6500	7000
Maximum Water/Cement Ratio (Note 2)						
lb/lb	0.443	0.488	0.577	Note 1	Note 1	Note 1
gals/bag	5.0	5.5	6.5	Note 1	Note 1	Note 1
Minimum Cement Content						
lb/cy	611	564	658	Note 1	Note 1	Note 1
Bags/cy	6.5	6.0	7.0	Note 1	Note 1	Note 1

Note 1: According to PCI Manual, except as indicated in Note 2.

Note 2: The maximum water/cement ratio for all classes of concrete except for Classes P, P-1 and P-2, when a Type F water-reducing, high range admixture is used according to Tables 914-1 and 914-2, shall be reduced by 0.043 lb/lb (4.5 gals/bag).

Note 3: All concrete test results shall be recorded to the nearest 10 psi..

Note 4: To successfully meet the requirements of this specification, the target production strength must be higher than the Class Design Strength by an amount proportional to the Producer's within-lot standard deviation.

Table 914-4 Lot Sizes, Sampling Rates and Retest Limits

	Class of Concrete					
	A	B	S	P	P-1	P-2
Lot Size (maximum)	One Day's Production			One Day's Production of a Single Steam Bed		
Pay-Adjustment Items						
Initial Sampling Rate	5/Lot	5/Lot	--	5/Lot	5/Lot	5/Lot
Retest Sampling Rate (minimum)	5/Lot	5/Lot	--	5/Unit or Load Test		
Non-Pay-Adjustment Items						
Initial Sampling Rate	3/Lot	2/Lot	1/Lot	3/Lot	3/Lot	3/Lot
Retest Limit (psi)	4400	3600	2000	5400	5900	6400
Retest Sampling Rate	5/Lot	5/Lot	5/Lot	5/Lot	5/Lot	5/Lot

Note 1: The lot sizes are maximums and, at the option of the Engineer, any lot may be subdivided into two or more smaller lots. When such a subdivision is made, the specified sampling rate applies to each of the smaller lots.

- Note 2: An initial strength test result is defined as the average strength of two 4 inch by 8 inch compression test cylinders, cured for 28 days, and tested in the Department Laboratory except for Classes P, P-1, and P-2 cylinders which may be tested at the fabricator's plant under the supervision of the Engineer.
- Note 3: A retest result is defined as the strength of an individual test result obtained by coring or other suitable means. If retest is performed by coring, each retest result is defined as the corresponding nominal core strength divided by 0.85.
- Note 4: The specified sampling rates shall apply except that no more than one test per truckload or batch of concrete will be required (except for air and slump tests when retempering). It is expected that each structural component will have a representative sample taken. At the option of the Engineer, nonstructural concrete lots consisting of 20 cubic yards or less may be accepted without strength tests.
- Note 5: No lot shall include more than one class of concrete nor include concrete of the same class having different specified levels of slump or air entrainment.
- Note 6: For prestressed concrete, if more than one bed is used or if more than 80 cubic yards of concrete are used, the production shall be subdivided as equally as possible into two or more lots.
- Note 7: Retest limit for non-pay-adjustment roadway and structural items requiring the use of Class B, white concrete, shall be 3000 psi.

The changes to SI2001M1 are as follows:

SECTION 106 – CONTROL OF MATERIAL

106.04 Materials, Inspections, Tests, and Samples.

THE FOLLOWING SUBPART IS ADDED:

- E. Sharing of Pay-adjustments for Portland Cement Concrete.** Positive and negative pay-adjustments, as defined in Subsection 914.02, Subpart E, are awarded to encourage high quality construction and, when necessary, to recoup the anticipated extra costs to the Department resulting from poor quality construction. The manner in which positive and negative pay-adjustments are to be shared by the prime Contractor and Subcontractors or Producers is to be negotiated by the affected parties. A letter signed by both parties, stating that an agreement has been reached between the parties shall be provided to the Engineer before commencement of Work. Nothing contained herein shall create right of action either in law or equity against the Department.

SECTION 305 – CONCRETE BASE COURSE

305.05 Opening to Traffic.

THIS SUBSECTION IS CHANGED TO:

The opening to traffic shall be as specified in Subsection 405.20.

SECTION 405 – CONCRETE SURFACE COURSE

405.08 Mixing Concrete.

1. Mixing on the Project in Truck Mixers.

THIS FIRST SENTENCE IN THE 15TH PARAGRAPH IS CHANGED TO:

Each batch shall be mixed not less than 50 revolutions at the rate of rotation designated as mixing speed.

3. Transit Mixing.

THE 9TH PARAGRAPH IS CHANGED TO:

Mixing shall begin immediately following the complete charging of the drum and continue for not less than 50 revolutions of the drum at the mixing speed recommended by the manufacturer of the truck mixer. Upon completion of at least the minimum number of mixing revolutions at the plant, the speed of the drum shall be reduced to the agitation speed recommended by the manufacturer.

THE LAST PARAGRAPH IS CHANGED TO:

Transit mix concrete will be rejected for any of the following reasons:

- e. If the concrete is not discharged within the specified time limit after loading all ingredients into the drum;
- f. If the indicator on the counter shows that the instrument has been turned off or tampered with;
- g. If the non-resettable total revolution counter shows more than 300 revolutions;
- h. If water has been added while the truck mixer is en route to the Project. Two-way telephone or radio communication between the site of the placement of concrete and the batching plant shall be provided.

914.02 Portland Cement Concrete Design, Control, and Acceptance Testing Requirements.

B. Proportioning and Verification.

THE SECOND SENTENCE OF THE THIRD PARAGRAPH IS CHANGED TO:

At least six 100 by 200 millimeter test cylinders shall be prepared from each batch and cured according to AASHTO T 23 or AASHTO T 126.

THE FIRST SENTENCE OF THE TENTH PARAGRAPH IS CHANGED TO:

Classes A and B concrete may be designed to achieve early strength requirements by increasing the Cement content.

C. Acceptance Testing Procedures for Slump and Air Entrainment.

THE FIRST SENTENCE OF THE FOURTH PARAGRAPH IS CHANGED TO:

Following any permitted additions, the drum shall be rotated at the recommended mixing speed for a minimum of 30 revolutions without exceeding 300 total revolutions, the original test results shall be disregarded, and a single test for both slump and air entrainment performed.

D. General Acceptance Testing Requirements for Strength.

THE FOLLOWING IS ADDED AFTER THE SECOND PARAGRAPH:

Concrete test specimens which are to be used for determination of early strengths for form removal, opening to traffic, or otherwise placing the concrete into service shall be cured according to the field curing provisions in AASHTO T-23.

E. Acceptance Testing for Strength for Pay-Adjustment Items.

THE ENTIRE TEXT OF THIS SUBPART IS CHANGED TO:

The list of concrete Pay Items, if any, which are subject to pay-adjustment and their base prices may be found in the Special Provisions.

The amount of pay-adjustment in dollars is the product of the Pay Item base price times the lot quantity times the percent pay-adjustment (expressed as a decimal) given by Equation 1 or Equation 2.

Equation 1 and Equation 2:

Quality

Pay-adjustment (Percent)

PD < 50	PPA = 3.0 - 0.3 PD	Equation 1
PD ≥ 50	PPA = 26.0 - 0.76 PD	Equation 2

Where: PPA = Percent Pay-adjustment
 PD = Percent Defective (Estimate of percent of lot below the class design strength by the use of Equation 3 and Subsection 914.05, Table 914-5)

Equation 3:

$$Q = (ALS - CDS) / S$$

Where: Q = Quality index for pay-adjustment computations
 ALS = Average lot strength in psi
 CDS = Class design strength in psi
 S = Standard deviation of the strength test results in psi for the lot as computed by Equation 4

Equation 4:

$$S = \sqrt{\frac{\sum(X_i - ALS)^2}{N - 1}}$$

Where: \sum = Summation
 Xi = Individual test result (average strength of a test cylinder pair)
 N = Number of test results for the lot

Note: When only a single test result is available, the standard deviation "S" is assumed to equal 2 Mpa.

For lots having percent defective (PD) levels less than 10 percent, Equation 1 provides positive adjustments to the contract price. For lots having exactly 10 percent defective, there is no adjustment to the contract price. For lots having greater than 10 percent defective, Equations 1 or 2, as appropriate, subtract progressively larger amounts from the contract price.

If, based on the initial series of tests, the lot quality of a pay-adjustment item is estimated to be PD = 50 or greater, or if any individual test value (average of a cylinder pair) falls below the retest limit for non-pay-adjustment concrete in Subsection 914.05, Table 914-4, the Engineer has the option to reevaluate by coring or other suitable means. When this provision is applied to Class P concrete, each beam or pile in the steam bed will be evaluated separately.

If the Department elects not to core, the Contractor may accept the pay-adjustment of (PPA) calculated by Equation 2 or, when approved by the Engineer, may take cores according to Subsection 914.05, Table 914-4 at no cost to the Department. The Contractor must take the cores within 60 days from notification of the option to core. As an aid in making this decision, the Contractor will be permitted to perform nondestructive testing using a method or device approved by the Engineer.

When re-evaluation is accomplished by a method other than coring, the results will be used only to determine what further action is to be taken. If any of the non-core tests results are below the class design strength, the Engineer has the option to core. If this option is waived, the Contractor may elect to core, at no cost to the State and within 60 days after being presented with this option, or to accept the pay-adjustment computed from the initial test cylinder results. If the Contractor elects to core, the coring shall be performed as directed and the Department will test the cores. If none of the non-core test results is below the class design strength, the Engineer may elect either to core or to accept the lot at 100 percent payment.

If, based on the core results, the lot is determined to be at a quality level of PD < 75, the pay-adjustment shall be computed by Equation 1 or Equation 2, as appropriate. If the lot is confirmed to be at a quality level of PD = 75 or greater, the lot is considered to be rejectable and the Engineer may:

1. Require the Contractor to remove and replace the defective lot at no cost to the State,
2. Allow the Contractor to leave the defective lot in place and receive a percent pay-adjustment (PPA) computed by Equation 2, or

4. Allow the Contractor to submit a plan, for approval, for corrective action to be performed at no cost to the State. If the plan for corrective action is not approved, either option 1 or 2 above may be applied.

F. Acceptance Testing for Strength for Non-Pay-Adjustment Items.

THE ENTIRE TEXT OF THIS SUBPART IS CHANGED TO:

All concrete items not specifically designated as pay-adjustment items as described in Subsection 914.02, Subpart E are considered to be non-pay-adjustment items, but may be accepted by pay-adjustment under certain circumstances. Such an item is eligible for 100 percent payment (PA = 0) provided the retest limit of Subsection 914.05, Table 914-4 is met. If this requirement is not met, the item will be treated as a pay-adjustment item according to Subsection 914.02, Subpart E, and all pay-adjustment provisions shall apply except that the item bid price will be used instead of an item base price in the computation of the pay-adjustment.

When a pay-adjustment is computed for any of the following items, which are only partially composed of concrete, the amount of pay-adjustment, if any, will be multiplied by the Estimated Percentage of Concrete (expressed as a decimal) as indicated below:

Pay Item of Concrete	Estimated Percentage
INLETS, TYPE ____	30
INLETS, TYPE ____, USING EXISTING CASTING	30
INLETS, TYPE B-____	40
INLETS, TYPE B-____, USING EXISTING CASTING	40
INLETS, TYPE ____ MODIFIED	40
INLETS, TYPE ____ MODIFIED, USING EXISTING CASTING	40
INLETS, TYPE ES	50
INLET CASTINGS, TYPE ES	40
MANHOLES	30
MANHOLES, ____ MM DIAMETER	30
MANHOLES, USING EXISTING CASTING	30
MANHOLES, SANITARY SEWER	30
MANHOLES, SANITARY SEWER, USING EXISTING CASTING	30
GRANITE CURB	25
RESET GRANITE CURB	25
BEAM GUIDE RAIL ANCHORAGES	25
CHAIN-LINK FENCE, ____ M HIGH	25
CHAIN-LINK FENCE, ALUMINUM-COATED STEEL, ____ M HIGH	25
CHAIN-LINK FENCE, PVC-COATED STEEL, ____ M HIGH	25
CHAIN-LINK FARM-TYPE FENCE	25
GATES, CHAIN-LINK FENCE, ____ M WIDE	25
GATES, CHAIN-LINK FENCE, ALUMINUM-COATED STEEL, ____ M WIDE	25
GATES, CHAIN-LINK FENCE, PVC-COATED STEEL, ____ M WIDE	25
GATES, CHAIN-LINK FARM-TYPE FENCE, ____ M WIDE	25
RESET FENCE	25
TEMPORARY CHAIN-LINK FENCE, ____ M HIGH	25
GUIDE SIGNS, TYPE GA, BREAKAWAY SUPPORTS	20
GUIDE SIGNS, TYPE GA, NON-BREAKAWAY SUPPORTS	20

The amount of pay-adjustment for pay items not listed above is the product of the unit bid price times the lot quantity times the percent pay-adjustment given by Equation 1.

914.04 Sampling and Testing Methods.

THE FOLLOWING AASHTO TEST METHOD IS ADDED:

T303 Standard Test Method for Accelerated Detection of Potentially Deleterious

Expansion of Mortar Bars Due to Alkali-Silica Reaction.

914.05 Tables

TABLES 914-1, 914-3, AND 914-4 ARE CHANGED TO:

Table 914-1 Requirements for Roadway Concrete Items

	Concrete Class	Slump (mm)	Percent Air Entrainment for Coarse Aggregate Size Numbers					
			357	467	57	67	8	
Cast-in-Place Items								
Surface Course, Bridge Approach Slabs, Bridge Approach Transition Slabs	B	50±25	5.0±1.5	5.0±1.5	6.0±1.5	6.0±1.5	7.0±1.5	
Base Course	B	50±25	5.0±1.5	5.0±1.5	6.0±1.5	6.0±1.5	7.0±1.5	
Inlet and Manhole Walls, Headwalls, Miscellaneous Concrete	B	75±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5	
Inlet and Manhole Top Slabs, Sidewalks, Driveways, Islands	B	75±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5	
Slope Gutters, Vertical Curb, Sloping Curb, Barrier Curb and Base	B	100±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5	
Concrete and White Concrete Vertical, Sloping and Barrier Curb, Concrete and White Concrete Islands	B	100±25	----	----	7.0±2.0	7.0±2.0	8.0±2.0	
Foundations for:								
Inlets and Manholes	B	75±25	6.5 max	6.5 max	7.5 max	7.5 max	8.5 max	
Electrical Items	B	75±25	----	----	7.5 max	7.5 max	8.5 max	
Signs	B	75±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5	
Junction Boxes	B	75±25	----	----	7.5 max	7.5 max	8.5 max	

Table 914-1 (Continued)

	Concrete Class	Slump (mm)	Percent Air Entrainment for Coarse Aggregate Size Numbers				
			357	467	57	67	8
Cast-in-Place Items (continued)							
Footings for Fence Posts, Guide Rail End Treatment	B	75±25	----	----	7.5 max	7.5 max	8.5 max
Culverts	A	75±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Monuments	A	75±25	----	----	7.5 max	7.5 max	8.5 max
Slope Protection	B	50±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Precast Items							
Culverts	A	75±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Inlets and Manholes, Junction Boxes, Headwalls, Reinforced Concrete End Sections (See note 2)	B	75±25	----	----	6.0±1.5	6.0±1.5	7.0±1.5
Concrete and White Concrete Barrier Curb	B	75±25	----	----	7.0±2.0	7.0±2.0	8.0±2.0

Note 1: According to Subsection 501.03, a Type F water-reducing, high range admixture will be permitted according to Subsection 905.02 and Subsection 914.02, Subparts B and C. When a Type F admixture is used, the table Slump and Air Content values for the given concrete item shall be changed as follows:

Slump: 150 ± 50 millimeters

Air Content: Increase both the target value and tolerance percentages by 0.5.

Note 2: For the items in this category, the slump may be reduced to zero (dry cast) provided that adequate consolidation, acceptable to the Engineer, is achieved.

Table 914-3 Mix Design Requirements

	Class of Concrete					
	A	B	S	P	P-1	P-2
Class Design Strength (28 days, Mpa Note 3)	32	26	14	38	42	45
Verification Strength (28 days, Mpa Note 3)	37	31	--	42	45	48
Maximum Water/Cement Ratio (Note 2)						
kg/kg	0.443	0.488	0.577	Note 1	Note 1	Note 1
L/bag	19	21	25	Note 1	Note 1	Note 1
Minimum Cement Content						
kg/m ³	363	335	391	Note 1	Note 1	Note 1
bags/m ³	8.5	7.8	9.2	Note 1	Note 1	Note 1

Note 1: According to PCI Manual, except as indicated in Note 2.

Note 2: The maximum water/cement ratio for all classes of concrete except for Classes P, P-1 and P-2, when a Type F water-reducing, high range admixture is used according to Tables 914-1 and 914-2, shall be reduced by 0.40 kg/kg (17.0 L/bag).

Note 3: All concrete test results shall be recorded to the nearest 0.10 Mpa.

Note 4: To successfully meet the requirements of this specification, the target production strength must be higher than the Class Design Strength by an amount proportional to the Producer's within-lot standard deviation.

Table 914-4 Lot Sizes, Sampling Rates and Retest Limits

	Class of Concrete					
	A	B	S	P	P-1	P-2
Lot Size (maximum)	One Day's Production			One Day's Production of a Single Steam Bed		
Pay-Adjustment Items						
Initial Sampling Rate	5/Lot	5/Lot	--	5/Lot	5/Lot	5/Lot
Retest Sampling Rate (minimum)	5/Lot	5/Lot	--	5/Unit or Load Test		
Non-Pay-Adjustment Items						
Initial Sampling Rate	3/Lot	2/Lot	1/Lot	3/Lot	3/Lot	3/Lot
Retest Limit (Mpa)	30	25	14	37	41	44
Retest Sampling Rate	5/Lot	5/Lot	5/Lot	5/Lot	5/Lot	5/Lot

Note 1: The lot sizes are maximums and, at the option of the Engineer, any lot may be subdivided into two or more smaller lots. When such a subdivision is made, the specified sampling rate applies to each of the smaller lots.

- Note 2: An initial strength test result is defined as the average strength of two 100 by 200 millimeter compression test cylinders, cured for 28 days, and tested in the Department Laboratory except for Classes P, P-1, and P-2 cylinders which may be tested at the fabricator's plant under the supervision of the Engineer.
- Note 3: A retest result is defined as the strength of an individual test result obtained by coring or other suitable means. If retest is performed by coring, each retest result is defined as the corresponding nominal core strength divided by 0.85.
- Note 4: The specified sampling rates shall apply except that no more than one test per truckload or batch of concrete will be required (except for air and slump tests when retempering). It is expected that each structural component will have a representative sample taken. At the option of the Engineer, nonstructural concrete lots consisting of 15 cubic meters or less may be accepted without strength tests.
- Note 5: No lot shall include more than one class of concrete nor include concrete of the same class having different specified levels of slump or air entrainment.
- Note 6: For prestressed concrete, if more than one bed is used or if more than 60 cubic meters of concrete are used, the production shall be subdivided as equally as possible into two or more lots.
- Note 7: Retest limit for non-pay-adjustment roadway and structural items requiring the use of Class B, white concrete, shall be 21 Mpa.

Instructions to Designers

The above specification revision shall be included for projects requiring Portland Cement Concrete that have been designed using the English or Metric 2001 Standard Specifications and are to be advertised after February 14, 2003. The specification revision has been incorporated in the Standard Inputs SI2001E1 and SI2001M1 updated as of February 7, 2003.

Designers may access updated versions of the Standard Inputs SI2001E1 and SI2001M1 from the following New Jersey Department of Transportation Web Page:

<http://www.state.nj.us/transportation/cpm/StandardInputs/standardinputs.htm>.

Distribution and Announcement Access Information

This announcement is being distributed electronically to our in-house staff and various public agencies based on our Standard Specifications distribution list maintained by the Engineering Documents Unit.

Internet access to this BDC Announcement can be downloaded and viewed from the following New Jersey Department of Transportation Web Page:

<http://www.state.nj.us/transportation/cpm/BaselineDocuments/T>.

Hard copies of this document can be acquired on a limited basis by contacting:

Engineering Documents Unit
E&O Building, 1st Floor
1035 Parkway Avenue, PO Box 600
Trenton, New Jersey 08625-0600
Phone: (609) 530-5587
Fax: (609) 530-6626

Recommended By:

Approved By:

ORIGINAL SIGNED

ORIGINAL SIGNED

Brian Strizki
Director,
Quality Management Services

Arthur Silber
Assistant Commissioner,
Capital Program Management

BJS:DES
☐ BDC02S-08.doc