

[Include the following where protective coating of sheeting is required.]

SECTION 416 PERMANENT SHEETING

416.04 PROTECTIVE COATING OF STEEL SHEETING

Replace the third sentence of the eighth paragraph with the following:

Provide a total system maximum dry film thickness of 16 mils for steel sheet piles.

SECTION 913 - PAINTS AND COATINGS

913.07 COAL TAR EPOXY COATING

Replace the entire subsection with the following:

Coal tar epoxy coating shall be a two-component, coal tar epoxy-polyamide paint (black) conforming to SSPC-Paint 16.