

DIVISION 900 – MATERIALS

[Include the following with contracts that include new or reconstructed inlets, manholes, tree wells, tree walls, or whenever concrete block material is specified:]

SECTION 916 – MASONRY UNITS

916.01 CONCRETE BLOCKS

Delete the second paragraph and replace it with the following:

Each block shall have a compressive strength of not less than 4,500 pounds per square inch (PSI) when tested in accordance with ASTM-C140.